



# TESTING LABORATORY DIRECTORATE EUROTEST-CONTROL EAD

108 Besarabia St, 1517 Sofia, tel. + 359 2 4470 360; tel./fax + 359 2 8720 596;  
[www.eurotest-control.bg](http://www.eurotest-control.bg), e-mail: [office@eurotest-control.bg](mailto:office@eurotest-control.bg)

QF 708-3/EN  
version 2/2018

## REPORT

№ 4 -0016 /21.05.2019

1. Rocks and minerals  
(product designation-type, brand, sort, etc.)
2. Customer: Vratza Stone Ltd  
(name and address of the customer)
3. Object: Career Vratsa Stone Ltd. area "Stanevi nivi".  
(description of the object/location of sampling)
4. Sampling: The sample has been provided by the customer.  
(number and date of the report of sampling, sampling method, deviations, additions to or exclusions from the sampling method)
5. Description of the samples: 1 sample  
(number, quantity, etc.)
6. Test method(s): БДС EN 12372:2008  
(identification of the test method(s) used)
7. Incoming number and date of receipt of the test sample(s): 944 / 02.05.2019  
(number and date of the request of testing)
8. Test performing period: 02.05.2019 to 21.05.2019

DIRECTOR OF  
TESTING LABORATORY DIRECTORATE:.....

/ Yuliana Akrabova /



## 9. Test results

Lab № 1904326, taken from career "Vratsa Stone" Ltd

| № | Measurand         | Unit | Measurement result |
|---|-------------------|------|--------------------|
| 1 | Flexural strength | MPa  | 17.9               |

NOTES: I. TLD is not responsible for the accuracy of sampling, sample storage life and sample storage conditions preceding submission to the laboratory.

HEAD OF DEPARTMENT:

/ eng. Valentin Tomov/

DIRECTOR OF TESTING

LABORATORY DIRECTORATE:

/ Yuliana AkraBova /

